

Claims

1. A transferable liquid crystal laminate comprising at least a releasable substrate, a protective layer and a cholesteric liquid crystal layer, the protective layer side of the releasable substrate having been subjected to an easily separable adhesive treatment.

2. The transferable liquid crystal laminate according to claim 1 wherein the peel strength between the releasable substrate and the protective layer is from 1.95 N/m to 19.5 N/m.

3. The transferable liquid crystal laminate according to claim 1 wherein the cholesteric liquid layer has on a part thereof diffractivity.